predict

Equipment Condition Report



Overall Diagnosis

London Offshore Consultants, Inc Att Tom Ronning 16800 Imperial Valley Drive, Suite 280 HOUSTON TX 77060 USA

Machine ID: Storage Tank Product (h/km): Lab Sample N°: GP708

Application: Machine (h/km): Label N°:

Make/Type:Filter (h/km):Equipment Ref. N°:LGP645Cust. Order N°:System (I):Sample Taken:15/09/2014Product:Shell Tellus T 32Top-up (I):Sample Received:25/09/2014

GP708 15/09/2014

Reported Maintenance:

unused lube oil.

Comments Oil Condition:

Visual aspect: yellow coloured, clear and bright, without visual foreign matter.

The water content is not significant: 70 ppm.

The kinematic viscosity @40°C, 31.95 mm²/s, complies with the mentioned ISO VG32 specification limit.

The kinematic viscosity @50°C is 22.22 mm²/s

The kinematic viscosity @60°C is 16.13 mm²/s

The kinematic viscosity @70°C is 12.14 mm²/s

The kinematic viscosity @100°C is 6.11 mm²/s

The oil's acidity is considered acceptable for this application: 0.57 mgKOH/g.

The ICP spectromertric results for the wear elements and silicon are all below the detection limit.

Comments Machine Condition:

The current WPC, 51.6 is too high for an unused sample.

The microscopic evaluation of the ferrogram shows small ferrous rubbing wear platelets, <15 µm.

We even found some larger ferrous fatigue chunks and flakes with a maximal diameter of 20µm.

Heat treatment shows that the ratio of low/medium alloy steel particles is approximately 70/30.

The present amount of dark magnetic iron oxides is remarkable, they are indicative for abnormal wear mode.

The non-ferrous wear mainly retains small blank metal particles, max 25µm.

The contaminant particles present mainly are crystalline particles (dust, sand), lube degradation products, polymeric matter.

Recommendations:

No rating as this is an unused sample from a storage tank, however the ferrographic analysis indicates larger wear particles and contaminant particles.

Ensure representative sampling!!!!!

Sample Reported: 26/09/2014 Nathalie De Vlam

Recommendations are advisory only and based on the assumption that equipment data and sample are accurate and representative of component being sampled.

predict







Test Name	Method	Unit	Results GP708
PHYSICAL-CHEMICAL ANALYSIS			
Colour	ASTM-D1500	-	1.5
/isual appearance	OMS 13882	-	clear
Determination of water (KF)	ASTM-D6304	ppm	70
Kinematic Viscosity @40°C	ASTM-D445	mm²/s	31.95
Kinematic Viscosity @100°C	ASTM-D445	mm²/s	6.110
Acid Number (AN)	ASTM-D664	mg KOH/g	0.57
ELEMENTAL ANALYSIS			
luminium	ASTM-D5185	ppm	0
Barium	ASTM-D5185	ppm	0
Calcium	ASTM-D5185	ppm	13
Chromium	ASTM-D5185	ppm	0
Copper	ASTM-D5185	ppm	0
ron	ASTM-D5185	ppm	0
Magnesium	ASTM-D5185	ppm	36
Molybdenum	ASTM-D5185	ppm	0
Sodium	ASTM-D5185	ppm	5
lickel	ASTM-D5185	ppm	0
Phosphorus	ASTM-D5185	ppm	290
.ead	ASTM-D5185	ppm	0
Silicon	ASTM-D5185	ppm	0
in	ASTM-D5185	ppm	0
Zinc	ASTM-D5185	ppm	311
Potassium	ASTM-D5185	ppm	1
WEAR INDEX		FF	
Optical density - large	OMS 13875	_	48.1
Optical density - small	OMS 13875	_	3.5
WPC - Wear Index	OMS 13875		51.6
% Large particles	OMS 13875	%	86
ANALYTICAL FERROGRAPHY	00	1,0	
FERROUS			
Rubbing wear	ASTM-D7690	µm max.	< 15
Severe sliding wear	ASTM-D7690 ASTM-D7690	µm max.	13
Abrasive wear	ASTM-D7690	µm max.	
Fatigue chunks	ASTM-D7690 ASTM-D7690	µm max.	20
Fatigue flakes	ASTM-D7690	µm max.	20
Spheres	ASTM-D7690 ASTM-D7690	µm max.	20
Dark oxides index	ASTM-D7690 ASTM-D7690	μπ max.	3
Red oxides - Rust index	ASTM-D7690		1
	ASTM-D7690	um may	'
Orrocive wear	173110-01030	μm max.	4
		-	
Ferrous wear - Severity index	OMS SWI 2.4	-	
Ferrous wear - Severity index NON-FERROUS	OMS SWI 2.4	um max	25
Ferrous wear - Severity index NON-FERROUS White metal alloy wear	OMS SWI 2.4 ASTM-D7690	μm max.	25
Ferrous wear - Severity index NON-FERROUS White metal alloy wear White metal alloy - Severity index	OMS SWI 2.4 ASTM-D7690 ASTM-D7690	-	25 2
Vhite metal alloy wear Copper alloy wear	OMS SWI 2.4 ASTM-D7690 ASTM-D7690 ASTM-D7690	μm max μm max.	
Ferrous wear - Severity index NON-FERROUS White metal alloy wear White metal alloy - Severity index Copper alloy wear Copper alloy index	OMS SWI 2.4 ASTM-D7690 ASTM-D7690 ASTM-D7690 ASTM-D7690	-	2
Vhite metal alloy wear Vhite metal alloy - Severity index Copper alloy wear Copper alloy index Non-FERROUS	OMS SWI 2.4 ASTM-D7690 ASTM-D7690 ASTM-D7690	- μm max.	
NON-FERROUS White metal alloy wear White metal alloy - Severity index Copper alloy wear Copper alloy index Non ferrous wear - Severity index CONTAMINANTS	OMS SWI 2.4 ASTM-D7690 ASTM-D7690 ASTM-D7690 ASTM-D7690 ASTM-D7690	- μm max.	2
NON-FERROUS White metal alloy wear White metal alloy - Severity index Copper alloy wear Copper alloy index Non ferrous wear - Severity index Contaminants Contaminants Contaminants	OMS SWI 2.4 ASTM-D7690 ASTM-D7690 ASTM-D7690 ASTM-D7690	μm max.	2
NON-FERROUS White metal alloy wear White metal alloy - Severity index Copper alloy wear Copper alloy index Non ferrous wear - Severity index CONTAMINANTS Crystalline particles index Amorphous particle index	ASTM-D7690 ASTM-D7690 ASTM-D7690 ASTM-D7690 ASTM-D7690 ASTM-D7690 ASTM-D7690	μm max. - -	2 2 3
White metal alloy wear White metal alloy - Severity index Copper alloy wear Copper alloy index Non ferrous wear - Severity index CONTAMINANTS Crystalline particles index Amorphous particle index Friction polymer severity index	ASTM-D7690 ASTM-D7690 ASTM-D7690 ASTM-D7690 ASTM-D7690 ASTM-D7690 ASTM-D7690 ASTM-D7690	μm max. - -	2 2 3 2 2
NON-FERROUS White metal alloy wear White metal alloy - Severity index Copper alloy wear Copper alloy index Non ferrous wear - Severity index CONTAMINANTS Crystalline particles index Amorphous particle index	ASTM-D7690 ASTM-D7690 ASTM-D7690 ASTM-D7690 ASTM-D7690 ASTM-D7690 ASTM-D7690	μm max	2 2 3

predict

Equipment Condition Report









non ferrous wear particle

larger ferrous wear





non ferrous wear and contaminant particles

contaminant particles